

DensArmor Plus®

High-Performance Interior Panel

Manufacturer

Georgia-Pacific Gypsum LLC
133 Peachtree Street
Atlanta, GA 30303
Technical Service Hotline: 1-800-225-6119

Georgia-Pacific Canada LP
6711 Mississauga Road,
Mississauga, ON L5N 2W3

Description

DensArmor Plus® High-Performance Interior Panels are a patented noncombustible (per ASTM E 136) interior panel that consists of a moisture-resistant gypsum core with coated fiberglass mats. The fiberglass mats provide superior protection from incidental moisture. DensArmor Plus panels are highly resistant to the growth of mold, scoring a 10, the highest score, when tested, as manufactured, per ASTM D 3273.

The core of DensArmor Plus panels is reinforced with fiberglass, increasing the product's strength. The treated core and the coated facings made with fiberglass offer greater moisture resistance and improved dimensional stability than regular gypsum board. The product resists warping, rippling and buckling.

They have a tapered edge to receive joint treatment. The field of the board can be finished in the same manner as regular gypsum board.

DensArmor Plus Interior Panels are the first drywall panels to be GREENGUARD Indoor Air Quality Certified® and GREENGUARD Children & SchoolsSM Certified for low emissions of volatile organic compounds (VOCs) by a leading third-party organization, GREENGUARD Environmental Institute. In addition, DensArmor Plus Interior Panels are the first drywall panels listed as GREENGUARD microbial resistant. This listing means DensArmor Plus panels, which feature fiberglass mats instead of paper facings used on the surface of traditional gypsum board products, resist mold growth. The microbial resistant test is based on ASTM Standard D 6329-98, a testing standard set by ASTM International, which develops testing guidelines and procedures for building materials, products, systems, and services.

DensArmor Plus panels also qualify for Collaborative for High Performance Schools® (CHPS™) credits. CHPS is a national non-profit organization that works with school districts and their design teams to improve the quality of education by using products that have met requirements to receive CHPS credits.

Primary Uses

DensArmor Plus Interior Panels are an interior wall or ceiling covering material for use in new construction or renovation work. They are designed for direct attachment with screws or nails to wood and metal framing or existing surfaces. They may be used as a covering material for flat or curved structures. DensArmor Plus panels are manufactured with fiberglass mat surfaces. They have a tapered edge to receive joint treatment. The field of the board can be finished in the same manner as regular gypsum board.

- Use on interiors of exterior walls, where moisture intrusion is most likely.
- Use in pre-rock areas, where the windows, doors or roof have not been installed making moisture intrusion inevitable. DensArmor Plus panels come with a 12-month limited warranty against normal weather exposure.*
- Georgia-Pacific Gypsum recommends the use of DensShield® Tile Backer in wet areas behind tile, such as tub and shower areas.

Limitations

DensArmor Plus Interior Panels are a non-structural product and should not be used as a nailing base to support heavy wall-mounted objects.

Intended for interior applications only, they must be kept dry during storage and handling.

Do not use DensArmor Plus® Fireguard® (per ASTM C 1658) panels where there is prolonged exposure to temperatures exceeding 125° F (52°C), e.g. adjacent to wood burning stoves, heating appliances, saunas or steam rooms.

Technical Data

Flame spread rating of 0 when tested in accordance with ASTM E 84 or CAN/ULC S-102. Scored a 10, the highest score, for resistance to the growth of mold when tested, as manufactured, according to ASTM D 3273.

Noncombustible as described and tested in accordance with ASTM E 136.

5/8" (15.9 mm) DensArmor Plus® Fireguard® and 1/2" (12.7 mm) DensArmor Plus® Fireguard C™ panels are UL and ULC Classified.

Decoration

DensArmor Plus Interior Panels are designed to accept most types of paints, textures and wall covering materials. Because of the enhanced moisture- and mold-resistant properties of DensArmor Plus panels, drying times for both joint compound and wall coverings may vary. Always follow paint or wall covering manufacturer's installation instructions when applying either of these finishes. Georgia-Pacific Gypsum strongly recommends priming the surface of DensArmor Plus panels with a quality, high solids primer/sealer before applying a final decorative material. Priming will equalize the suction variations between the joint compounds and the fiberglass surfaces. If glossy paints are used in such areas as kitchens or bathrooms, skim coat joint compound over the entire surface of DensArmor Plus panels to reduce highlighting or joint photographing. This method is also recommended in areas with severe natural or artificial side lighting.

Handling Precautions

See *Handling and Use—Caution* section at end of this document.

Stack DensArmor Plus High-Performance Interior Panel flat on a level surface. As individual sheets are removed for installation, they should be raised up on edge carefully and carried in a vertical position. Appropriate handling for gypsum board is also outlined in Gypsum Association Publications GA-216.

Take care to avoid impact, undue flexing and subsequent damage to board edges, ends and corners.

Note: Material Safety Data Sheet (MSDS) is available on request.

Applicable Standards

Manufactured to meet ASTM C 1658, ASTM C 1396 Section 7 and ASTM C 1177.

*For complete warranty details, visit www.gpgypsum.com.

continued →

Submittal Approvals

Job Name _____

Contractor _____

Date _____

Sizes and Edges

DensArmor Plus® Thickness: 1/2" (12.7 mm); Width: 4' (1219 mm); Lengths: 8'-12' (2438 mm-3658 mm); Edges: Tapered

DensArmor Plus® Fireguard C™ Thickness: 1/2" (12.7 mm); Width: 4' (1219 mm); Lengths: 8'-12' (2438 mm-3658 mm); Edges: Tapered

DensArmor Plus® Fireguard® Thickness: 5/8" (15.9 mm); Width: 4' (1219 mm); Lengths: 8'-12' (2438 mm-3658 mm); Edges: Tapered

Installation

DensArmor Plus High-Performance Interior Panels should be installed according to the most current versions of Gypsum Association Publication GA-216 "Application and Finishing of Gypsum Board for Non-Fire-Rated Construction."

For fire-rated installations, the installation and details shall be in conformity with those assemblies published in the Gypsum Association Fire Resistance Design Manual GA-600, UL and ULC Fire Resistance Directories.

Physical Properties

Properties	1/2" DensArmor Plus®	1/2" DensArmor Plus® Fireguard C™	5/8" DensArmor Plus® Fireguard® and Fireguard C™
Thickness, nominal	1/2" (12.7 mm) ± 1/64" (0.4 mm)	1/2" (12.7 mm) ± 1/64" (0.4 mm)	5/8" (15.9 mm) ± 1/64" (0.4 mm)
Width, standard	4' (1219 mm) ± 3/32" (2.4 mm)	4' (1219 mm) ± 3/32" (2.4 mm)	4' (1219 mm) ± 3/32" (2.4 mm)
Length, standard	8' (2438 mm) to 12' (3658 mm) ± 1/4" (6.4 mm)	8' (2438 mm) to 12' (3658 mm) ± 1/4" (6.4 mm)	8' (2438 mm) to 12' (3658 mm) ± 1/4" (6.4 mm)
Weight ¹ , lbs./sq. ft., nominal (kg/m ²)	2.02 ¹ (9.9)	2.2 ¹ (10)	2.5 ¹ (12.2)
Edges	Tapered	Tapered	Tapered
Surfacing	Coated fiberglass mat on face, back	Coated fiberglass mat on face, back	Coated fiberglass mat on face, back
Flexural strength, parallel, lbf. (N)	>80 (356)	>80 (356)	>100 (444)
Flexural strength, perpendicular, lbf. (N)	>100 (444)	>100 (444)	>140 (622)
R Value ² °F•ft ² •hr/BTU (K•m ² /W)	.56 (0.099)	.56 (0.099)	.67 (0.118)
Nail pull resistance minimum, lbf. (N)	80 (356)	80 (356)	90 (400)
Hardness core, edges and ends, lbf. (N)	>15 (67)	>15 (67)	>15 (67)
Water absorption (% of weight)	<5%	<5%	<5%
Surface burning characteristics (per ASTM E 84 or CAN/UL-S102): flame spread/smoke developed	0/0	0/0	0/0
Humidified deflection	2/8" (6.4 mm)	2/8" (6.4 mm)	1/8" (3 mm)
Bending Radius ³	6' (1829 mm)	6' (1829 mm)	8' (2438 mm)

¹ Represents approximate weight for design and shipping purposes.

² Tested in accordance with ASTM C 518.

³ Double fasteners on ends as needed.

NOTE: Specified minimum value are as in ASTM C 1658 and applicable standards of ASTM C 1177, ASTM C 1396 Section 7.



U.S.A. – Georgia-Pacific Gypsum LLC
Canada – Georgia-Pacific Canada LP

SALES INFORMATION AND ORDER PLACEMENT

U.S.A. Midwest: 1-800-876-4746 West: 1-800-824-7503
South: 1-800-327-2344 Northeast: 1-800-947-4497

CANADA Canada Toll Free: 1-800-387-6823
Quebec Toll Free: 1-800-361-0486

TECHNICAL INFORMATION

U.S.A. and Canada: 1-800-225-6119
www.gpgypsum.com

TRADEMARKS Unless otherwise noted, all trademarks are owned by or licensed to Georgia-Pacific Gypsum LLC. GREENGUARD, and GREENGUARD Children & Schools are registered certification marks used under license through the GREENGUARD Environmental Institute. CHPS is a trademark owned by Collaborative for High Performance Schools, Inc.

WARRANTIES, REMEDIES AND TERMS OF SALE For current warranty information for this product, please go to www.gpgypsum.com and select the product for warranty information. All sales of this product by Georgia-Pacific are subject to our Terms of Sale available at www.gpgypsum.com.

UPDATES AND CURRENT INFORMATION The information in this document may change without notice. Visit our website at www.gpgypsum.com for updates and current information.

CAUTION For product fire, safety and use information, go to www.gp.com/safetyinfo or call 1-800-225-6119.

HANDLING AND USE—CAUTION This product contains fiberglass facings which may cause skin irritation. Dust and fibers produced

during the handling and installation of the product may cause skin, eye and respiratory tract irritation. Avoid breathing dust and minimize contact with skin and eyes. Wear long sleeve shirts, long pants and eye protection. Always maintain adequate ventilation. Use a dust mask or NIOSH/MSHA approved respirator as appropriate in dusty or poorly ventilated areas.

FIRE SAFETY CAUTION Passing a fire test in a controlled laboratory setting and/or certifying or labeling a product as having a one-hour, two-hour, or any other fire resistance or protection rating and, therefore, as acceptable for use in certain fire rated assemblies/systems, does not mean that either a particular assembly/system incorporating the product, or any given piece of the product itself, will necessarily provide one-hour fire resistance, two-hour fire resistance, or any other specified fire resistance or protection in an actual fire. In the event of an actual fire, you should immediately take any and all actions necessary for your safety and the safety of others without regard for any fire rating of any product or assembly/system.